

ABSTRACT OF THE DISCLOSURE

A method of forming a roughened, decontaminated surface on a metal article which includes the single or multiple blasting of the surface with a chilled iron grit of appropriate roughness structure followed by acid pickling to produce a contamination free surface of substantially S_q 5 to 10 microns.

477276_1.DOC